

Factory Applied Facings

Product is available to order with wide ranges of factory applied facings such as various grades of aluminium foil, glass cloth, glass matt, polyester laminate.

Fire Performance

Fibertex-350 achieves four zero Early Fire Hazard Indices when tested in accordance with AS 1530:Part 3-1976 (same as BS 476 : Part 5, 6, 7-1967) for non-combustible material.

Ignitability	(0-20)	0
Spread of Flame	(0-10)	0
Heat Evolved	(0-10)	0
Smoke Developed	(0-10)	0

Moisture Resistance

Exposure to an atmosphere of 50 °C and 95% relative humidity for 96 hours results in moisture absorption of less than 0.2% by volume. Should insulation become wet, full thermal efficiency will be restored on drying out. Water repellent grade according to BS 2792 section 12 is available to order.

Corrosion Resistance

Fibertex-350 is faintly alkaline and is incapable of corroding steel, copper, or aluminium. To maintain this condition, protection must be provided against contamination from external sources. When tested in accordance with BS 3958: Part 5-1969, results in range of pH 7.5 - 8.0. Fibertex-350 contains less than 15ppm soluble chlorides. For critical applications involving austenitic stainless steel, a low chloride formulation is available to order.

Acoustic Properties

When tested in a reverberation chamber in accordance with AS 1045-1971, sound absorption coefficients of Fibertex-350 are shown in the table:


Thickness (mm)	Centre Frequency (Hz)							
	125	250	500	1000	2000	4000	5000	NRC [†]
25	0.18	0.29	0.69	0.86	1.05	1.20	1.16	0.71
50	0.29	0.70	1.19	1.04	1.14	1.06	1.07	0.93

NRC[†] is the average sound absorption coefficient between 250 to 2000 Hz .

Compression Resistance

Fibertex-350 is a resilient insulation material which readily recovers to original shape after removal of compressive load.

The graph shows the reduction in thickness (%) under compressive load (kPa), measured in accordance with BS 2972 -1975.



Reduction in nominal thickness (%)
x compressive loading (kPa)

CSR Bradford Rockwool technology is well accepted and recognised by the insulation industry throughout the world. Our sales and technical executives are well trained and always prepared to offer assistance and advice on all inquiries.

CSR Insulation (Thailand) Ltd.**Thailand Factory / Head Office**

Eastern Industrial Estate
1 Soi G2, Pakornsongkroraj Road
Huay Pong, Muang, Rayong 21151, Thailand.
Phone: (66 38) 685 110 Fax: (66 38) 684 938

Bangkok Office

52/160 Soi Pracharuamjai
Krungthep-Kreetha Road, Sapansoong
Bangkok 10250, Thailand.
Phone: (66 2) 736 0924 Fax: (66 2) 736 0934

WE HELP CONSERVE ENERGY

CSR web site : <http://www.csr.com.au>

The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Bradford Insulation. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification. The purchaser should independently determine the suitability of the product for the intended use and application. B1060205

