

Titanium BA-101

TYPE BA01-01 (BA101)

SPECIFICATION

TiO₂ content	:	98%	min
Color (compared with standard sample)	:	Not lower than	
Lightening power (Compared with standard sample)	:	100%	min
Matter volatile at 105°C (after 24 h preconditioning at 23± 2°C and (50± 5)%RH)	:	0.5%	max
Matter soluble in water	:	0.5%	max
PH of aqueous suspension	:	6.0 – 8.0	
Oil Absorption, g/100g sample	:	26%	max
Residue on 45 µm sieve	:	0.1%	max
Resistivity of aqueous extract Ω m	:	20	min
Usage	:	Chiefly used in rubber, plastic, paper, ink, glass and innerwork paint industry etc.	
Packing	:	In plastic lined plastic woven bag of 25 kgs net each.	

www.nicinterchem.com

" Being your partner and growing together "

26/26 Moo 4 Suksawat Road., Jomthong, Jomthong, Bangkok Thailand 10150

Mobile Phone 086-781-2907 / Fax 02-942-8900 # 1020 Email sales@nicinterchem.com

Lampang Tel / Fax 054-222-1118