

Yellow Iron Oxide 313 (New)

Iron yellow oxide use in paint, plastic, rubber, cement product ,
construction outside coating , etc.

SPECIFICATION

Properties	Value
Apearance	Yellow powder
Fe ₂ O ₃	86% min
105C Moisture	1.0% max
Water soluble salts	0.3% max
Residue on 320 mesh sieve	0.3% max
pH Value	3.5-8
Oil absorption	25-35 g/100g
Tinting Strength	95-105%
Colour difference vs standard	1.0 max
Tamped apparent density	0.4-0.5 g/cm ³
Density	4.0-4.3 g/cm ³
Particle shape	Acicular , Predom acicular
Packing	25 Kgs/Bag
Source	China

www.nicinterchem.com

" Being your partner and growing together "

26/26 Moo 4 Suksawat Road., Jomthong, Jomthong, Bangkok Thailand 10150

Mobile Phone 086-781-2907 / Fax 02-942-8900 # 1020 Email sales@nicinterchem.com

Lampang Tel / Fax 054-222-118